

Лакопласт Р								
№ п/ п	Оттенок	Колор-индекс	Свето- стойкость	Атмосферо- стойкость	Термо- стойкость, Сº	Устойчивость к действию		
						кислот	щелочей	раство- рителя
1		PW 6	8	5	200	5	5	5
2		PY 13	6	4-5	230	5	5	5
3		PY 34 средний жёлтый	7	5	200	4	3	5
4		PY 34 лимонный	7	5	200	4	3	5
5		PY42	8	5	180	4-5	5	5
6		PY 62	7	5	240	4	3-4	5
7		PY 83	5-6	4-5	200	5	5	5
8		PY 191	7-8	4-5	290	5	5	5
9		PO 13	6	2-3	180	5	5	3-4
10		PO 16	6	4-5	200	4-5	4-5	5
11		PO 17	4	3-4	270	4-5	2	5
12		PR 101	8	5	280	4-5	5	5
13		PR 170 (F3RK)	7-8	4	220	4	5	5
14		PR 170 (F5RK)	7	4	200	4	5	5
15		PR 176	8	5	260	5	5	5
16		PR 254	8	5	300	5	5	4-5
17		PR 48:2	5	4	240	4-5	4-5	4-5
18		PR 53:1	4	4-5	200	4-5	4-5	4-5
19		PR 57:1	4-5	4	240	4-5	2-3	5
20		PR 122	7-8	4-5	250	5	5	5
21		PV 23	7-8	5	200	5	5	5
22		PBI 29	8	5	400	3	5	5
23		PBI 15:1	8	4-5	280	5	5	5
24		PBI 15:3	8	4-5	280	5	5	5
25		PG 7	8	4-5	280	5	5	5
26		PG 17	8	5	600	5	5	5
27		PBr 6	8	5	200	5	5	5
28		PBk 7	8	5	200	5	5	5