

Apactive™ Dyes For Wool & Silk Chloro Bromo Derivatives (производные)

Apactive™ Dyes For Wool & Silk	CI №	Yellow 4G (Yellow 39)	Red B (Red 65)	Red 5B (Red 66)	Red 6G (Red 84)	Scarlet 3G (Red 136)	Blue 3R (Blue 50)	Blue 3G (Blue 69)
Treatment Suitability	Carbonising	▼▼	▼▼	▼▼	▼▼	▼▼	▼▼	▼▼
	Decastising	▼	▼▼	▼	▼▼	▼▼	▼▼	▼▼
	Dry Cleaning	▼▼	▼▼	▼▼	▼▼	▼▼	▼▼	▼▼
	Dischargeabilty	▼▼	▼▼	▼	▼	▼	⌀	⊗
	1/12	5-6	5-6	4-5	5	4	5	5
	1/3	6	5-6	5	5-6	4-5	5	5-6
	1/1	7	6	5-6	5-7	5-6	6	6-7
	2/1	7-8	7	6-7	7	6	6-7	6-7
Washing Fastness	CO6/B2, 50° C	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5
	IWS TM 250/ 40° C	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5
	Water IWS TM 6	4-5 4-5	4-5 4-5	4-5 4-5	5 5	4-5 4-5	4-5 4-5	4-5 4-5
	Hot Water 70° C	4-5 4-5	4-5 4-5	4-5 4-5	5 5	4-5 4-5	4-5 4-5	4-5 4-5
Staining of Multifibre strip	PAN	4-5	4-5	4-5	4-5	4-5	4-5	4-5
	PES	4-5	4-5	4-5	5	4-5	4-5	4-5
	CO	4-5	4-5	4-5	4-5	4-5	4-5	4-5
Rub Fastness ISO 105x12	Dry	4-5	4-5	4-5	4-5	4-5	4-5	4-5
	Wet	4	4	4	4	4	4	4
Solubility (g/l)	90° C	100	100	100	100	100	100	100
	60° C	100	80	70	60	100	100	100
	Solution Solubility 60° C	100	100	70	60	100	100	100
Fastness to other aqueous								
Miling Alkaline	Ch	3-4	4-5	4-5	4	4	4-5	4
	Wo	4-5	4-5	4-5	5	5	4	4
	CO	4-5	3-4	4	5	5	5	5
Cross Dyeing Acetic Acid	Ch	4-5	4-5	5	5	5	4-5	4-5
	Wo	4	3-4	4	4-5	4-5	3-4	4
	Co	5	5	5	5	5	5	5
Perspiration Acid Eo4		4-5	4-5	4-5	4-5	4-5	4-5	4-5
		4-5	4-5	4-5	4-5	4-5	4-5	4-5
Perspiration Alkaline Eo4		4-5	4-5	4-5	4-5	4-5	4-5	4-5
		4-5	4-5	4-5	4-5	4-5	4-5	4-5