

Apactive™ RGB

Aptive™ RGB		General Properties							Fastness Properties								
		Substantivity	Suitability			Dischargeability	Washing off Properties	Solubility g/l at 30°C	Light Fastness (AATCC/16E, 20AFU)		Washing					Perspiration	
			Exhaust 60°C	Cold Pad Batch Silicate	Pad Dry-Pad Steam						I.S.O.3		I.S.O.4				
									1%	3%	Effect	Stain	Effect	Stain	Chlorinated Water (20 ppm active)	Alkaline	Acidic
Yellow RGB		H	▼	▼	▼	G	G	100	4	4	4	5	5	5	2-3	5	5
Red RGB		H	▼	▼	▼	⊗	G	100	3	4	5	5	4	4-5	3	5	5
Blue RGB		H	▼	▼	▼	G	G	100	3	3-4	5	4-5	4-5	4-5	2-3	5	5
Dark Blue RGB		H	▼	▼	▼	G	G	100	3	3-4	5	4-5	4-5	4-5	2-3	5	5
Navy RGB		H	▼	▼	▼	G	G	100	3	3-4	4	5	4	4-5	2	5	5

▼ Recommended ⊗ Not recommended H Suitable Hight G Good Fair