

Apactive™ RR

Apactive™ RR		1/1 Standart Depth	Migration Index (%)	Level Dyeing Factor (%)	Reactivity Index T ₅₀ (min)	Fixation Yield (%)	Process Suitability			Post Mercerize	Washing Fastness		Light Fastness (AATCC/16E, 20 AFU)					Crock Fastness		Solubility (G/L)			Post Fastness Properties					
							Exhaust	Cold Pad Batch	Post Bleach		CO6/E2	C4A	1/25	1/12	1/6	1/3	1/1	Dry	Wet	30°C	60°C	+60 gpl Salt	Chlorinated Water (ISO 105)	Hydrogen Peroxide (ISO 105 N02)	Hydrolysis (M&S C11)	Mercerizing (ISO 105x04)	Perspiration Acid (E04)	Perspiration Alkali (E04)
Yellow RR		3.61	90	75	13	84	Recommended	Highly Recommended	Recommended	Recommended	4-5	4-5	4	4	4	4	4-5	4-5	4	175	180	120	4-5	3-4	4-5	4-5	4-5	4-5
Red RR		4.20	98	90	12	86	Recommended	Highly Recommended	Recommended	Recommended	4-5	4-5	4	3-4	3-4	4	4-5	4-5	4	175	200	125	3-4	3-4	4-5	4-5	4-5	4-5
Blue RR		4.00	96	91	14	92	Recommended	Highly Recommended	Recommended	Not recommended	4-5	4-5	3	3-4	3-4	4	4	4-5	4-5	170	180	160	4-5	4-5	4-5	4-5	4-5	4-5

Recommended

Highly Recommended

Not recommended