

Apactive™ S																												
Apactive™ S Series		1/1 Standart Depth	Migration Index (%)	Level Dyeing Factor (%)	Reactivity Index T ₅₀ (min)	Fixation Yield (%)	Process Suitability			Dischargeability	Washing Fastness		Light Fastness (AATCC/16E, 20 AFU)					Crock Fastness		Solubility (G/L)			Post Fastness Properties					
							Exhaust	Cold Pad Batch	Continuous		CO6/E2	C4A	1/25	1/12	1/6	1/3	1/1	Dry	Wet	30°C	60°C	+60 gpl Salt	Chlorinated Water (ISO 105 E03) 20ppm	Hydrogen Peroxide (ISO 105 N02)	Hydrolysis (C11)	Mercerizing (ISO 105x04)	Perspiration Acid (E04)	Perspiration Alkali (E04)
Yellow S3R		1.71	82	80	12	85	▼	▼	▼	▼	4-5	4-5	4	4	4	4	4-5	4-5	4	175	180	120	4 4-5	3-4 4	4 4-5	4-5 4-5	4-5 4-5	4-5 4-5
Deep Red SB																												
Red S2B																												
Red S2G																												
Navy SGI		6.00	90	80	12	85	▼	▼	▼	▼	4-5	4-5	2-3	2-3	3	3-4	4	4	3-4	175	200	75	3 3-4	4-5 4	3-4 4	4 4	4 4	3-4 3-4
Dark Blue SGL		3.00	85	80	13	86	▼	▼	▼	⊗	4-5	4-5	3	3-4	4	4	4-5	4-5	4	165	175	110	4 4-5	4 4	4 4-5	4-5 4	4-5 4-5	4-5 4-5

▼ Recommended ⊗ Not recommended ⊘ Limited interest