

Aрactive™ W (от светлого до тёмного оттенка)																													
Aрactive™ W Series		1/1 Standart Depth	Migration Index (%)	Level Dyeing Factor (%)	Reactivity Index T ₅₀ (min)	Fixation Yield (%)	Process Suitability			Dischargeability	Washing Fastness		Light Fastness (AATCC/16E, 20 AFU)					Crock Fastness		Solubility (G/L)		Post Fastness Properties							
							Exhaust	Cold Pad Batch	Continuous/ e-Dyeing		CO6/C2S 60°C	CO6/C2S 95°C	1/25	1/12	1/6	1/3	1/1	Dry	Wet	30°C	+60 gpl Salt	Water Fastness (ISO 105 E01)	Chlorinated Water (ISO 105 E03)	Oxidative Bleach (M&S C10A)	Hydrolysis (M&S C11)	Mercerizing (ISO 105x04)	Perspiration Acid (E04)	Perspiration Alkali (E04)	
Orange W3R																													
Red WB																													
Red WIN																													
Dark Blue WIR																													
Bril. Blue WBR		6.70	88	80	12	85	▼	▼	▼	▼	4-5 4-5	4-5 4	4	4	4	4	4	4-5	4-5	200	80	4-5 4-5	4	40T	4 4-5	4-5 4	4-5 4-5	4-5 4-5	
Navy Blue WB		6.30	88	86	12	92	▼	▼	▼	▼	4-5	4-5	–	–	–	3	4	4	3-4	170	125	4 4-5	4 4	40T	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5	
Black WNN		6.26	88	86	12	92	▼	▼	▼	▼	4-5	4-5	–	–	3	3-4	4	4-5	3-4	170	125	4 4-5	4	40T	4 4	4-5 4	4-5 4-5	4-5 4-5	

▼ Recommended

⊗ Not recommended