


Лакопласт PU								
№ п/ п	Оттенок	Колор-индекс	Свето-стойкость	Атмосферо-стойкость	Термо-стойкость, Сº	Устойчивость к действию		
						кислот	щелочей	растворителя
1		PW 6	8	5	200	5	5	5
2		PY 13	6	4-5	230	5	5	5
3		PY 17	6	5	230	5	5	5
4		PY 34 средний жёлтый	7	5	200	4	3	5
5		PY 34 лимонный	7	5	200	4	3	5
6		PY 42	8	5	180	4-5	5	5
7		PY81	7-8	5	240	5	5	5
8		PY 83	5-6	4-5	200	5	5	5
9		PY 191	7-8	4-5	290	5	5	5
10		PO 13	6	2-3	180	5	5	3-4
11		PO 16	6	4-5	200	4-5	4-5	5
12		PO 36	8	5	260	5	5	5
13		PR 104	6	5	220	4	2	5
14		PR 170 (F3RK)	7-8	4	220	4	5	5
15		PR 170 (F5RK)	7	4	200	4	5	5
16		PR 176	8	5	260	5	5	5
17		PR 254	8	5	300	5	5	4-5
18		PR 53:1	4	4-5	200	4-5	4-5	4-5
19		PR 57:1	4-5	4	240	4-5	2-3	5
20		PV 23	7-8	5	200	5	5	5
21		PBI 29	8	5	400	3	5	5
22		PBI 15:1	8	4-5	280	5	5	5
23		PBI 15:3	8	4-5	280	5	5	5
24		PG 7	8	4-5	280	5	5	5
25		PBr 6	8	5	200	5	5	5
26		PBk 7	8	5	200	5	5	5