

Direct		C.I.No (Direct)	Dyeing Depth o.w.f%	Fastness				
Color Shade	Product Name			Light (xenou)	Washing (40°C)	Hot Pressing 200°C	Rubbing	
							Dry	Wet
	Blue 3RL 100%	BI 67	1.4	5-6	2-3	3	4	3
	Blue RGL 100%	BI 70	1.7	4-5	4	3	3-4	3
	Blue B2RL 100%	BI 71	2.1	5-6	3-4	3	4	2-3
	Blue 2GL 200%	BI 75	5.0	5	3-4	4-5	4	3-4
	Sky Blue G 250%	BI 78	2.0	5	2-3	3	3-4	2-3
	Blue 2RL 200%	BI 80	1.6	6	2-3	4	4	2-3
	Turq. GL 100%	B 86	3.0	6-7	2	5	3-4	2
	Navy Blue BLE 100%	B 94	2.0	7	4-5	4	4-5	4
	Grey CGL 100%	BK 112	3.0	6	4	3	4-5	3
	Black ANBN 100%	BK 166	3.0	4	2-3	4-5	4	3
	Black HEF 150%	BK 168	3.0	5	4-5	5	4-5	4
	Black D-BR 100%	BK 173	8.0	3-4	4-5	4-5	3	2
	Black G 100%	BK 19	4.5	4	4-5	3	4	2
	Black GF 150%	BK 22	4.5	5-6	4	2-3	4-5	3
	Brown S-BR 100%	Mix	1.8	3-4	3-4	–	3-4	2-3
	Orange 6R 150%	O 102	3.0	3	4	4-5	4-5	4
	Orange TGL 182%	O 34	1.0	5-6	3	3	3-4	3
	Orange 2GL 200%	O 39	1.0	6-7	4	3	4-5	3-4
	Red F2G 100%	R 224	2.2	3-4	4-5	4-5	3-4	3
	Rose FR 100%	R 227	2.2	3	4-5	4-5	4	3
	Red 2G 150%	R 239	2.2	5	4-5	4	4	3-4
	Red BWS 100%	R 243	2.0	5	4-5	4	3-4	3
	Red 8BN 100%	R 254	3.0	4	1-2	4-5	4-5	2-3
	Scarlet 4GE 100%	R 277	2.2	4	4-5	3-4	4	3
	Pink BK 100%	R 75	1.9	5	3-4	3-4	4-5	3
	Red 4BL 170%	R 79	1.2	6	3	3-4	3-4	3
	Red F3B 150%	R 80	2.3	5	3	3-4	3	3
	Red 4B 150%	R 81	1.7	4	4	2-3	4-5	3
	Yellow GL 200%	Y 147	3.0	6	3-4	4-5	5	3-4
	Yellow 6GF 100%	Y 157	1.1	5	2	4	4-5	2-3
	Yellow D-3RNL 100%	Y 161	1.0	4	4-5	4-5	4-5	4
	Yellow AGL 100%	Y 169	0.9	5	3-4	4	4	3-4
	Yellow GLE 100%	Y 177	1.0	5	3-4	4	4	3-4
	Yellow GR 100%	Y 24	1.5	4	4-5	4-5	4	2-3
	Brill. Yellow 2G 100%	Y 26	1.5	4	1	4	4-5	4
	Yellow 5GL 100%	Y 27	3.0	5	1	5	5	4
	Yellow FF 200%	Y 28	1.5	6	3	4	4	3-4
	Yellow GC 182%	Y 44	1.0	4-5	3	3-4	4-5	3
	Yellow RS 100%	Y 50	1.3	5	2-3	3-4	4	3
	Yellow L-5R 100%	Y 83	1.1	6	4-5	4	3	2-3
	Yellow D-RL 100%	Y 86	1.1	6	2-3	4	4-5	3