


Normal Direct Dyes								
Direct		C.I.No (Direct)	Dyeing Depth o.w.f%	Fastness				
Color Shade	Product Name			Light (xenou)	Washing (40 ⁰ C)	Hot Pressing 200 ⁰ C	Rubbing	
							Dry	Wet
	Blue BH 180%	Bl 2	1.5	3-4	4	4	2-3	2
	Sky Blue 5R 100%	Bl 15	3.6	1-2	2-3	3	4-5	3
	Cooper Blue 2R 100%	Bl 151	0.8	5	2-3	3	4-5	3
	Blue 2B 100%	Bl 6	2.1	2-3	2-3	3	4-5	2-3
	Grey D 100%	BK 17	2.0	2	3	3	4	3
	Black EX 100%	BK 38	4.0	4	4	4	4	1-2
	Black OB 200%	BK 80	4.5	3-4	3	4	4	3
	Brown N-D3G	Br 1	1.5	2	4-5	3-4	4	2
	Dark Brown MM 100%	Br 2	1.8	3-4	3-4	2-3	4-5	2
	Brown 3G 150%	Br 44	1.8	2	2	4	4	3
	Green BE 100%	G 1	1.5	3	3	4	4-5	2-3
	Yellow Brown MD 100%	Mix	2.4	2	2	4	4	2-3
	Red Brown RN 100%	Mix	1.5	2-3	3-4	3	4-5	2-3
	Dark Brown ME 100%	Mix	1.5	3-4	3-4	2-3	4-5	2
	Yellow G 100%	Y 6	1.0	1-2	2-3	4	4-5	3
	Flavin 7GFF 500%	Y 96	1.5	1-2	2-3	3-4	4-5	4