

Direct		C.I.No (Direct)	Dyeing Depth o.w.f%	Fastness				
Color Shade	Product Name			Light (xenou)	Washing (40°C)	Hot Pressing 200°C	Rubbing	
							Dry	Wet
	Chestnut Brown 431	Mix	2.0	3-4	3-4	2-3	3	3
	Grey GL 200%	Mix	1.2	3	3-4	3	4-5	3
	Orange S 150%	O 26	3.0	3	4	4-5	4-5	3-4
	Red 4B 200%	R 2	1.5	–	–	–	–	–
	Red 6B 200%	R 16	3.0	2	1-2	4-5	4	3
	Scarlet 4BS 150%	R 23	0.7	2-3	3	3	4-5	2
	Pink 12B 100%	R 31	0.6	2	3	2	4	2
	Black BX	Replace of BK 38	5.0	5-6	4-5	4-5	4-5	3
	Violet N 100%	V 1	1.5	3-4	3	4	3-4	2-3
	Violet BK 150%	V 9	1.3	2	1-2	1	4-5	3
	Yellow NBP 100%	Y 4	1.5	2-3	2	2-3	4	2-3
	Yellow R 150%	Y 11	1.5	3-4	2-3	4	4	2-3
	Chrysophenine G	Y 12	3.0	4	2-3	4-4	4-5	3
	Yellow 5G 100%	Y 8	1.5	2	1-2	3-4	3-4	2-3