

Direct Fast Dyes								
Direct		C.I.No (Direct)	Dyeing Depth o.w.f%	Fastness				
Color Shade	Product Name			Light (xenou)	Washing (40°C)	Hot Pressing 200°C	Rubbing	
							Dry	Wet
	Brill. Blue BL 200%	BI 106	1.6	6-7	3-4	3-4	4-5	3
	Blue FFRL	BI 108	3.0	6	4	3	4-5	3
	Truq. Blue FBL 200%	BI 199	2.2	6-7	3	3	3-4	2-3
	Blue 4BL 200%	BI 200	1.1	6	4	4	4-5	3
	Blue BRL 200%	BI 201	3.0	6-7	3	4-5	4-5	4
	Blue 4G 100%	BI 202	3.0	6	3	4-5	4	3-4
	Blue RCL 100%	BI 203	2.0	5-6	4	4	5	3
	Blue 3G 100%	BI 218	2.2	5-6	5	4	4-5	4
	Blue 219 100%	BI 219	1.5	–	–	–	–	–
	Blue BWL 143%	BI 237	4.0	6	4-5	4	5	3
	Blue D-3GL 100%	BI 274	1.0	4	4-5	4-5	4-5	4-5
	Dark Blue D-3GL 100%	BI 297	4.0	3	3-4	4	4	2-3
	Brill. Blue GL 160%	BI 293	3.0	5	4	4	5	4-5
	Blue BFF 100%	BI 311	2.0	5	3	3-4	5	4
	Black VSF 600	BK 22	4.5	6	4-5	2-3	4-5	3
	Grey LBN 200%	BK 56	1.5	4	3	4	4-5	3
	Grey 4GL 300%	BK 62	2.8	6	4	3-4	4	3-4
	Brown 3G 150%	Br 44	1.5	2	2	3-4	4	3
	Brown BRS 150%	Br 95	1.5	–	–	–	–	–
	Brown 102 100%	Br 102	1.5	–	–	–	–	–
	Brown AGL 100%	Br 115	2.0	6	2	3-4	3-4	3
	Brown RL 130%	Br 116	2.0	6	2-3	–	3-4	3-4
	Brown GTL 100%	Br 210	2.4	7	4-5	4-5	4	3
	Brown 422 100%	Br 422	1.5	–	–	–	–	–
	Brown 494 100%	Br 494	1.5	–	–	–	–	–
	Green BLE 155%	G 26	1.7	6	4	3	4	3
	Green 5GL 145%	G 28	2.6	4-5	2	2	4-5	2-3
	Red 3BNL 100%	Mix	2.0	5	3	3	4-5	2
	Red BL 100%	R 83	3.0	6	4	4-5	4-5	4
	Rubine BL 100%	R 83:1	1.9	6-7	3-4	3	3-4	2-3
	Scarlet BNL 200%	R 89	2.2	5-6	2	3	5	2
	Pink B 100%	R 9	1.0	4	4	4	4-5	3-4
	Blend Violet D-BL 100%	V 35	1.5	2	2	–	–	–
	Violet BB 100%	V 51	2.0	4	1.2	–	2	1-2
	Violet 5BL 100%	V 66	2.2	6-7	2	4	4-5	3
	Violet 4BL 250%	V 66	0.9	6-7	2	4	4-5	3
	Violet MB 150%	V 9	4.0	4-5	3-4	4-5	4	3-4
	Yellow L3R 154%	Y 106	3.0	5	4	4-5	5	3-4
	Yellow G 330%	Y 107	0.9	7	2-3	4-5	4	3
	Yellow GR 330%	Y 120	0.9	4	3-4	4	4-5	4
	Yellow 3GF 330%	Y 132	0.9	4-5	3-4	4	4	3
	Yellow PG 100%	Y 142	1.0	4-5	3-4	4	4	3